




COMPACTED ROPE - 6STRAND IWRC (STEEL CORE)



6 x P.F1 {29:1+7+(7)+14} + IWRC

6 x P.WS {31:1+6+(6+6)+12} + IWRC

6 x P.WS {36:1+7+(7)+14} + IWRC

Nominal diameter		Min. Breaking strength						Approx. Weight		Max. Length
Inch	mm	KISWIRE - HIGH (200G)			KISWIRE - SUPER (220G)			kg/m	Lbs/ft	m
		Tonnef	kN	lb	Tonnef	kN	lb			
	10	8.6	84	18,900	9.1	90	20,100	0.474	0.318	2,000
7/16	11.1	10.3	101	22,700	10.9	107	24,000	0.570	0.383	3,050
	12	12.0	118	26,500	12.8	126	28,200	0.682	0.458	3,050
1/2	12.7	13.5	132	29,800	14.3	140	31,500	0.749	0.503	3,050
	13	14.1	138	31,100	15.0	147	33,100	0.785	0.527	3,050
9/16	14.3	17.2	169	37,900	18.3	179	40,300	0.950	0.638	2,000
5/8	16	21.4	210	47,200	22.8	224	50,300	1.180	0.793	3,050
	18	27.1	266	59,700	28.9	283	63,700	1.490	1.000	3,050
3/4	19.1	30.5	299	67,200	32.5	319	71,600	1.680	1.130	3,050
	20	33.4	328	73,600	35.6	349	78,500	1.840	1.240	3,050
	22	40.5	397	89,300	43.2	424	95,200	2.230	1.500	3,050
7/8	22.2	42.0	412	92,600	44.5	436	98,100	2.270	1.530	3,050
	24	48.2	473	106,300	51.4	504	113,300	2.650	1.780	2,440
	25	52.3	513	115,300	55.8	547	123,000	2.890	1.940	2,440
1	25.4	54.0	530	119,000	57.6	565	127,000	2.980	2.000	2,440
	26	56.6	555	124,800	60.4	592	133,200	3.120	2.100	2,000
	28	65.6	643	144,600	70.0	686	154,300	3.610	2.430	2,000
1-1/8	28.6	68.5	672	151,000	73.1	717	161,200	3.770	2.530	2,000
	30	75.4	739	166,200	80.4	788	177,200	4.150	2.790	3,450
1-1/4	31.8	84.7	831	186,700	90.4	887	199,300	4.660	3.130	3,000
	32	85.7	840	188,900	91.5	897	201,700	4.720	3.170	3,000
	34	96.8	949	213,400				5.330	3.580	2,700
1-3/8	35	103.0	1,010	227,100				5.610	3.770	2,400
	36	109.0	1,069	240,300				5.970	4.010	2,400
	38	121.0	1,187	266,800				6.690	4.500	2,400
	40	134.0	1,314	295,400				7.380	4.890	2,400